



Thermoplastic Hot Melt Adhesive for bonding and strengthening.

Description

Main raw materials:	Polyethylene, polypropylene and petroleum resins		
Type:	Polyolefin (PO)	Odor:	Odorless
State:	100% Solid	Solubility:	Water-immiscible
Shape:	Brick	Toxicity:	Non-toxic
Size:	≈ 9 x 6 x 14 cm	Reactivity:	Not found
Color:	White	Flammable:	If expose to flame
Translucency:	Translucent	Self igniting:	No

Properties

Properties	Value	Method
Viscosity:	3000 ± 500 cps/180°C	GB/T 15332 (R&B)
Softening Point:	100 ± 5 °C	HG/T 3360
Density:	0.942 ± 0.005 g/cm³	ASTM D792-20
Setting time:	1200–1800 s	HMA-05-10 (Poseidon)

Instructions

Operation Temperature:	box 155 - 165 °C	tube / gun body
Equipment:	Hot Melt Machine	
Storage:	Well-ventilated place, away from direct sunshine.	

Applications

Filter material composite

Bonding and strengthening of Paper packaging

Shoe's external to internal materials bond

Bonding and strengthening of filter structure

Notice

- Open time is changeable, depending upon the nature of the substrate, application temperature, the adhesive applied, room temperature and closing pressure.
- All surfaces should be clean and free of loose elements.
- The color of the product may be have some differences due to different batches of raw material, but it will not affect the physical properties.
- The properties data in this table are typical values, and not guaranteed specification.



热可塑性热熔胶, 适用于粘接和复合。

描述

主要原料:	聚乙烯、聚丙烯和石油树脂	
类型:	聚烯烃 (PO)	气味: 无味
状态:	100% 固体	溶解度: 不溶于水
外观:	块状	毒性: 无毒
尺寸:	≈ 9 x 6 x 14 cm	反应性: 未找到
颜色:	白色	易燃: 如果暴露在火焰中
半透明:	半透明	自燃: 不

物性

	规格值	方法
熔融粘度:	3000 ± 500 cps/180°C	GB/T 15332 (R&B)
软化点:	100 ± 5 °C	HG/T 3360
密度:	0.942 ± 0.005 g/cm ³	ASTM D792-20
固化时间:	1200~1800 s	HMA-05-10 (Poseidon)

使用建议

建议操作温度:	胶箱 155 - 165 °C	胶管/枪体
设备:	热熔胶机	
贮存:	通风良好的地方, 远离阳光直射。	

应用

过滤材料复合	适用于纸品包装结构粘接和加固
鞋的外部与内部材料粘合	
适用于过滤器结构粘接和加固	

注意事项

- 开放和固化时间会随胶温及环境温度 涂布量 贴合时间和压力等而改变;
- 使用前请将基材表面处理干净;
- 应充分重视物质安全数据表;
- 产品色泽可能会因为原料批次不同而产生一定差异, 但不会影响物性。

Guangzhou POSEIDON Material Technology Co., LTD

广州波塞冬材料科技有限公司

总部: 广州市南沙区东涌镇马骏街89号哲铭科创园2栋

电子邮件 电子邮件 info@poseidon-group.net

www.poseidon-group.net / www.poseidon-group.cn

电话: 86 - 20 3466 7266

传真: 86 - 20 3112 3266